

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
22 April 2004 (22.04.2004)


PCT

(10) International Publication Number  
**WO 2004/033736 A1**

- (51) International Patent Classification<sup>7</sup>: C22B 34/12, B22F 9/28, C22C 1/04
- (21) International Application Number: PCT/US2003/027651
- (22) International Filing Date: 3 September 2003 (03.09.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 60/416,630 7 October 2002 (07.10.2002) US
- (71) Applicant (for all designated States except US): INTERNATIONAL TITANIUM POWDER, LLC. [US/US]; 20634 W. Gaskin Drive, Lockport, IL 60441 (US).
- (72) Inventors; and  
(75) Inventors/Applicants (for US only): ANDERSON, Richard [US/US]; 5836 Sunrise Avenue, Clarendon Hills, IL 60514 (US). ARMSTRONG, Donn [US/US]; 6005 Ridge Court, Lisle, IL 60532 (US). JACOBSEN, Lance [US/US]; 123 San Carlos Road, Minooka, IL 60447 (US).
- (74) Agent: LEVY, Harry, M.; Emrich and Dithmar, 300 South Wacker Drive, Suite 3000, Chicago, IL 60606 (US).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),

[Continued on next page]

(54) Title: SYSTEM AND METHOD OF PRODUCING METALS AND ALLOYS



(57) Abstract: A system and method of producing an elemental material or an alloy from a halide of the elemental material or halide mixtures. The vapor halide of an elemental material or halide mixtures are introduced into a liquid phase of a reducing metal of an alkali metal or alkaline earth metal or mixtures thereof present in excess of the amount needed to reduce the halide vapor to the elemental material or alloy resulting in an exothermic reaction between the vapor halide and the liquid reducing metal. Particulates of the elemental material or alloy and particulates of the halide salt of the reducing metal are produced along with sufficient heat to vaporize substantially all the excess reducing metal. Thereafter, the vapor of the reducing metal is separated from the particulates of the elemental material or alloy and the particulates of the halide salt of the reducing metal before the particulate reaction products are separated from each other.

WO 2004/033736 A1



Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,  
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,  
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

**Published:**

— *with international search report*